## Quantum Transport Evidence for the Three-Dimensional Dirac Semimetal Phase in Cd<sub>3</sub>As<sub>2</sub> and Observation of Superconductivity under High Pressure

L. P. He<sup>1</sup>, Y. T. Jia<sup>2</sup>, S. J. Zhang<sup>2</sup>, X. C. Hong<sup>1</sup>, J. K. Dong<sup>1</sup>, J. Pan<sup>1</sup>, Z. Zhang<sup>1</sup>, J. Zhang<sup>1</sup>, C. Q. Jin<sup>2\*</sup> and S. Y. Li<sup>1\*\*</sup>

1Department of Physics, Surface Physics Laboratory (National Key Laboratory), and Laboratory of Advanced Materials, Fudan University, Shanghai 200433, China 2Beijing National Laboratory for Condensed Matter Physics and Institute of Physics,

Chinese Academy of Sciences, Beijing 100190, China

## Abstract

We report the quantum transport properties of  $Cd_3As_2$  single crystals in a magnetic field. A large linear quantum magnetoresistance is observed near room temperature. With decreasing temperature, the Shubnikov—de Haas oscillations appear in both the longitudinal resistance  $R_{xx}$  and the transverse Hall resistance  $R_{xy}$ . From the strong oscillatory component  $\Delta R_{xx}$ , a linear dependence of the Landau index n on 1/B is obtained, and it gives an n-axis intercept between 1/2 and 5/8. This clearly reveals a nontrivial  $\pi$  Berry's phase, which is a distinguished feature of Dirac fermions. And the resistance of Cd3As2 under pressure up to 50.9 GPa was also measured. Surprisingly, superconductivity with  $T_c \approx 2.0$  K emerges at 8.5 GPa. The  $T_c$  keeps increasing to about 4.0 K at 21.3 GPa, then shows an anomalous nearly constant pressure dependence up to the highest pressure 50.9 GPa. Our observation of superconductivity in pressurized three-dimensional Dirac semimetal Cd<sub>3</sub>As<sub>2</sub> provides an interesting candidate for topological superconductor.



## Berry's Phase







Left: (a) The oscillatory component  $\Delta Rxx$ , extracted from Rxx by subtracting a smooth background. A single oscillation frequency F  $\approx 58.3$  T is identified from FFT. (b) The temperature dependence of the relative amplitude of  $\Delta Rxx$  for the 6th Landau level. The solid line is a fit to the LK formula, which gives m<sup>\*</sup>  $\approx 0.044$ m<sub>0</sub> and v<sub>F</sub>  $\approx 1.1 \times 10^6$  m/s.

Right: (a) The high-field oscillatory components  $\Delta R_{xx}$  and  $\Delta R_{xy}$  at 1.5 K. The  $\Delta R_{xy}$  oscillations are phase shifted approximately by 90°. (b) Landau index n plotted against 1/B. The closed circles denote the integer index ( $\Delta R_{xx}$  valley), and the open circles indicate the half integer index ( $\Delta R_{xx}$  peak). The index plot can be linearly fitted, giving the intercept 0.58 ± 0.01. The measurements of another single crystal labeled as sample B give a similar intercept 0.56 ± 0.03, which is strong evidence for a nontrivial  $\pi$  Berry's phase of 3D Dirac fermions in Cd<sub>3</sub>As<sub>2</sub>[1,2,3].

## H<sub>c2</sub> and Phase Diagram











Left: The superconducting transition of the  $Cd_3As_2$  single crystal at (a) 11.7 GPa and (b) 13.5 GPa in magnetic fields applied perpendicular to the (112) plane. (c) Temperature dependence of the upper critical field  $H_{c2}$ . The dashed line is a linear fit to the data, which points to  $H_{c2}(0) \approx 4.29$  T for 13.5 GPa.

Top: Phase diagram of  $Cd_3As_2$  showing the superconducting transition temperature  $T_c$  as a function of pressure. This phase diagram is similar to that of 3D topological insulator  $Bi_2Se_3$ [4]. [1] Z. K. Liu, J. Juan *et al.*, Nat. Mater. **13**, 677 (2014).

[2] Y. B. Zhang, Y.W. Tan, H. L. Stormer, and P. Kim, Nature (London) **438**, 201 (2005).

[3] H. Murakawa *et al.*, Science **342**, 1490 (2013).

[4] K. Kirshenbaum *et al.*, Phys. Rev. Lett. **111**, 087001 (2013).

In summary, we have performed bulk transport measurements on single crystals of the proposed 3D Dirac semimetal Cd3As2. A large linear quantum magnetoresistance is observed nearroom temperature. By analyzing the Shubnikov-de Haas oscillations of longitudinal resistance at low temperature, a nontrivial  $\pi$  Berry's phase with a small phase shift is obtained, which provides bulk quantum transport evidence for the existence of a 3D Dirac semimetal phase in Cd3As2. We have done resistance measurements on the 3D Dirac semimetal Cd3As2 single crytals under pressures up to 50.9 GPa. Below 6.4 GPa, the resistance behavior becomes more and more insulating with increasing pressure, however it changes back to metallic again at higher pressures. Superconductivity emerges at 8.5 GPa. The Tc increases from 2.0 K at 8.5 GPa to 4.0 K at 21.3 GPa, then it shows an anomalous constant pressure dependence up to the highest pressure measured.

> Phys. Rev. Lett. 113, 246402 (Editor's Suggestion) (2014) arXiv:1502.02509 (2015)